


## technical datasheet

# Heritage

### 1. Product description

- |                            |   |
|----------------------------|---|
| 1.1. Format                | 665 x 133 x 8 mm  |
| 1.2. Packing               | 14 boards each pack = 1,24 m <sup>2</sup>   |
| 1.3. Technical description |   |
| - Surface                  | Three-dimensional interlaced melamine resin   |
| - Decor                    | Melamine resin impregnated printed paper  |
| - Core layer               | HDF High Density Fiberboard   |
| - Balance film             | Melamine resin impregnated paper  |
| 1.4. Installation          | Mechanical looking system , Clic-System – much easier to install , up to 50% quicker to install (against other clic systems). Floating installation according to the installation description . |
| 1.5. Classification        | ISO 10874      class 23 : heavy domestic use<br>class 32 : heavy commercial use<br><br>EN 14041 CE – Mark   |
| 1.6. Fire classification   | EN 13501      C <sub>fl</sub> – s1 (Hardly inflammable ~ B1)  |
| 1.7. Emission              | E1 lower than 0,05 ppm  |
| 1.8. Slip resistance       | Technical class DS  |
| 1.9. Thermal conductivity  | Thermal resistance according to DIN EN 12667 R= 0,063 [(m <sup>2</sup> * K)/W]  |



# Heritage

	Characteristic	Requirements	Unit	Testmethod
1.	Sampling			EN 13329
2.	Thickness	8	mm	EN 13329
3.	Level of use	21 - 32		EN 13329
4.	Wear resistance	AC4		EN 13329
5.	Impact resistance	IC2		EN 13329
6.	Thickness swelling 24h	≤ 12	%	EN 13329
7.	Resistance to staining	5,g. 1-2 4,g. 3		EN 438
8.	Internal blond	> 1,2	N/mm <sup>2</sup>	EN 319
9.	Surface soundness	> 1,5	N/mm <sup>2</sup>	EN 311
10.	Surface layer width	± 0,1	mm	EN 13329
11.	Surface layer length	± 0,3	mm	EN 13329
12.	Squareness	max 0,2	mm	EN 13329
13.	Surface layer straightness	< 0,3	mm/m	EN 13329
14.	Height difference between elements	max 0,15	mm	EN 13329
15.	Openings between elements	max 0,2	mm	EN 13329
16.	Formaldehyd content	<0.05	ppm	EN 717-1

Erstellt (Datum, Unterschrift)  QS	Geprüft und Freigegeben (Datum, Unterschrift)  11.03.2021 Schmaltz	
---	---	--